


Braided Double Insulated PVC/PVC Triple Twisted Flex Product Range: *BTPP*



SCHEMATIC DRAWING

3 core construction



CABLE CONSTRUCTION

1. Viscose Rayon braid
2. TI3 type PVC outer insulation
3. TI2 type PVC inner insulation
4. Electrolytic tinned flexible copper conductor

APPLICATIONS

This product is designed for use as a pendant drop or table and floor lamps. Approval for rise and fall applications should be confirmed with ourselves prior to adoption.

<u>Characteristics</u>	
Rated Voltage:	300 V _{ac}
Test Voltage:	2500 V _{ac}
Temperature Range:	-20 °C ÷ 90 °C
Short-circuit Temperature:	160 °C
Minimum Bending Radius:	10 x Overall Diameter

Revision Date:
21/07/2022

Issue No.
1.2

Page:
1 of 2

In order to improve our products, the information contained in this technical datasheet can be changed without notice. Please check periodically with our office, the date and issue number.

Size Conductor [mm ²]	Conductor Stranding [N° x mm]	Electrical Resistance [Ω/Km]	Diameter on Insulation		Radial Thickness of Insulation	
			1 st Insulation	2 nd Insulation	1 st Insulation	2 nd Insulation
			[mm]		[mm]	
0.50	19 x 0.183	≤ 39.0	1.4 ± 0.1	1.9 ± 0.1	≥ 0.25	≥ 0.25
0.75	19 x 0.224	≤ 26.7	1.7 ± 0.1	2.2 ± 0.1	≥ 0.30	≥ 0.25

Flexform Product Code	Size Conductor [mm ²]	Outer Diameter [mm]
BTPP-303	3 x 0.50	4.7 ± 0.5
BTPP-403	3 x 0.75	5.3 ± 0.5

All versions of this cable can be ordered with a plain or patterned viscose rayon textile braid, available in over 60 colours.
Please contact us for a list of available colours.

Cable Standards

Low Voltage European Directive No. 2014/35/UE.

Stranding of Conductor

Class 5 electrolytic tinned flexible copper conductor, conforming to IEC 60228 requirements.

Inner Insulation

TI2 type PVC conforming to EN 50363-3 requirements, hardness: (92 ± 2) Sh-A.

Outer Insulation

Transparent TI3 type PVC conforming to EN 50363-3 requirements, hardness: (87 ± 2) Sh-A. The outer covering will not be separable from the inner insulation.

Cable Assembly

The cores are braided in viscose rayon before being twisted together.

Core Identification

3 Core: Brown ●, Blue ● and Green/Yellow ●

Revision Date:
21/07/2022

Issue No.
1.2

Page:
2 of 2

In order to improve our products, the information contained in this technical datasheet can be changed without notice. Please check periodically with our office, the date and issue number.